DATA SHEET


Milled Fiber MF 7904



LANXESS

Energizing Chemistry

| Polymer | PTFE and others | | |
|---------------------|---|--------------------------------|--|
| | LANXESS Glass Fiber MF 7904 [*] is suitable for a wide range of applications where the reinforcing properties of glass fiber are needed in combination wit very small initial fiber length, no surface treatment and excellent flowability. I can be used, for example, for the reinforcement of polytetrafluoroethylene. | | |
| Product Description | Very small initial average fiber length of 50 μm (nominal) | | |
| | No surface treatment / sizing | | |
| | | | |
| | | | |
| Technical | Fiber Diameter (nom.) | 14 µm | |
| Characteristics | Av. Fiber Length (nom.) | 50 µm | |
| | Glass | E-Glass (DIN 1259) | |
| | Size | - | |
| | Moisture content | ≤ 0,05 wt% | |
| | Bulk density | approx.920 kg / m ³ | |
| | (Original data ex works) | | |
| Packaging | Cardboard box, Octabin (see detailed information on next page) | | |
| Storage | The glass fiber should be stored in a dry place, preferably at room tempera- ture and 50 - 70 % relative humidity. | | |
| Contact | For further information please contact: | | |
| | Mail | glassfiber@lanxess.com | |
| | Phone | +49 (0)221 8885 7275 | |
| | | | |



DATA SHEET



Packaging Information MF 7904

| ardboard box with plastic bag | | Octabin | | |
|-------------------------------|------------------------|--------------------|-----------------------|--|
| Net Weight Box | 25 kg | Net Weight | 750 kg | |
| Net Weight Pallet | 1000 kg (40 boxes) | Dimensions Octabin | 1086 x 1086 x 870 mm | |
| Dimensions Box | 390 x 290 x 275 mm | Dimensions Pallet | 1140x1140x138 mm (CP3 | |
| Dimensions Pallet | 1000x1200x138 mm (CP1) | Packaging Code | ZK 75 | |
| Packaging Code | ZX 00 – RA100D | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |

Disclaimer

Values

Unless specified to the contrary, the values given have been established on standardized test. The figures should be regarded as guide values only and not as binding minimum values.

© = LANXESS Deutschland GmbH | HPM Business Unit | all rights reserved www.glassfiber.lanxess.com Page 2 of 2 | Edition 14.12.2020

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.