

Durethan AKV30XTS2 901510

PA 66, 30% glass fibers, injection molding, heat-aging stabilized, high temperature stabilized, improved surface finish

ISO Shortname: ISO 16396-PA 66+PA 6I,GF30,GHR,S14-100

Property	Test Condition	Unit	Standard	guide value d.a.m.	cond.
Rheological properties					
C Molding shrinkage, parallel	60x60x2	%	ISO 294-4	0.35	
C Molding shrinkage, transverse	60x60x2	%	ISO 294-4	0.7	
Post- shrinkage, parallel	60x60x2	%	ISO 294-4	0.1	
Post- shrinkage, transverse	60x60x2	%	ISO 294-4	0.18	
Mechanical properties (23 °C/50 % r. h.)					
C Tensile modulus	1 mm/min	MPa	ISO 527-1,-2	10000	6500
C Tensile Stress at break	5 mm/min	MPa	ISO 527-1,-2	190	120
C Tensile Strain at break	5 mm/min	%	ISO 527-1,-2	3	7.5
C Charpy impact strength	23 °C	kJ/m ²	ISO 179-1eU	60	95
C Charpy impact strength	-30 °C	kJ/m ²	ISO 179-1eU	50	45
C Charpy notched impact strength	23 °C	kJ/m ²	ISO 179-1eA	<10	12
C Charpy notched impact strength	-30 °C	kJ/m ²	ISO 179-1eA	<10	<10
Izod impact strength	23 °C	kJ/m ²	ISO 180-1U	50	75
Izod impact strength	-30 °C	kJ/m ²	ISO 180-1U	50	50
Izod notched impact strength	23 °C	kJ/m ²	ISO 180-1A	<10	12
Flexural modulus	2 mm/min	MPa	ISO 178-A	9500	6500
Flexural strength	2 mm/min	MPa	ISO 178-A	280	195
Flexural strain at flexural strength	2 mm/min	%	ISO 178-A	3.8	6.5
Flexural stress at 3.5 % strain	2 mm/min	MPa	ISO 178-A	270	160
C Puncture maximum force	23 °C	N	ISO 6603-2	750	920
C Puncture maximum force	-30 °C	N	ISO 6603-2	700	715
C Puncture energy	23 °C	J	ISO 6603-2	2.4	3.8
C Puncture energy	-30 °C	J	ISO 6603-2	2.2	2.1
Ball indentation hardness		N/mm ²	ISO 2039-1	225	
Thermal properties					
C Melting temperature	10 °C/min	°C	ISO 11357-1,-3	260	
C Temperature of deflection under load	1.80 MPa	°C	ISO 75-1,-2	235	
C Temperature of deflection under load	0.45 MPa	°C	ISO 75-1,-2	250	
Vicat softening temperature	50 N; 120 °C/h	°C	ISO 306	235	
C Coefficient of linear thermal expansion, parallel	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	0.23	
C Coefficient of linear thermal expansion, transverse	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	0.9	
Electrical properties (23 °C/50 % r. h.)					
C Comparative tracking index CTI	Solution A	Rating	IEC 60112	600	
Other properties (23 °C)					
C Water absorption (Saturation value)	Water at 23 °C	%	ISO 62	6.3	
C Density		kg/m ³	ISO 1183	1380	
Bulk density		kg/m ³	ISO 60	630	
Processing conditions for test specimens					
C Injection molding-Melt temperature		°C	ISO 294	290	



Durethan AKV30XTS2 901510

Property	Test Condition	Unit	Standard	guide value <small>d.a.m.</small>	<small>cond.</small>
C Injection molding-Mold temperature		°C	ISO 294	80	
Processing recommendations					
Drying temperature dry air dryer		°C	-	80	
Drying time dry air dryer		h	-	2-6	
Residual moisture content		%	Acc. to Karl Fischer	0.03-0.12	
Melt temperature (Tmin - Tmax)		°C	-	270-290	
admissible residence time at Tmax		min	-	<5	
Mold temperature		°C	-	80-100	

C These property characteristics are taken from the CAMPUS plastics data bank and are based on the international catalogue of basic data for plastics according to ISO 10350.



Durethan AKV30XTS2 901510

Disclaimer

Disclaimer for trial products

This is a trial product at the developmental stage. No definitive statements can therefore be made as to type conformity, processability, long-term performance characteristics or other production or application parameters. Therefore, the purchaser/user uses the trial product entirely at his own risk without having been given any warranty or guarantee and agrees that the supplier shall not be liable for any damage, of whatever nature, arising out of such use. Unless specified to the contrary, the values given have been established on standardized test specimens at room temperature. The figures should be regarded as non-binding approximate data only, and not as guide values or binding minimum values. Please note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mold/die, the processing conditions and the coloring. The marketing and continued supply of this material are not assured and may be discontinued at any time. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Processing note

Under the recommended processing conditions small quantities of decomposition product may be given off during processing. To preclude any risk to the health and well-being of the machine operatives, tolerance limits for the work environment must be ensured by the provision of efficient exhaust ventilation and fresh air at the workplace in accordance with the Safety Data Sheet. In order to prevent the partial decomposition of the polymer and the generation of volatile decomposition products, the prescribed processing temperatures should not be substantially exceeded. Since excessively high temperatures are generally the result of operator error or defects in the heating system, special care and controls are essential in these areas.

Conditioning

Conditioning in accordance with ISO 1110 (70 °C; 62 % r.h.)

LANXESS DEUTSCHLAND GMBH | D - 50569 COLOGNE

© LANXESS Deutschland GmbH

