

## Durethan BC304 000000

PA 6, non-reinforced, injection molding, improved impact strength

ISO Shortname: ISO 16396-PA 6-I,,GR,S14-020

Property	Test Condition	Unit	Standard	guide value <sup>1</sup>	
				dry as molded	conditioned
Mechanical properties (23 °C/50 % r. h.)					
Tensile modulus	1 mm/min	lb/in²	ASTM D 638	261000	116000
Tensile stress at yield	-	lb/in²	ASTM D 638	6520	5080
Tensile elongation at yield	-	%	ASTM D 638	4.0	
Tensile elongation at break	-	%	ASTM D 638	> 200	> 200
Izod notched impact strength	73 °F, 0.125 in	ft-lb/in	ASTM D 256	12.1	17.2
Izod notched impact strength	-40 °F; 0.125 in	ft-lb/in	ASTM D 256	12.1	12.1
Flexural modulus	-	lb/in²	ASTM D 790	232000	109000
Flexural stress at 5 % strain		lb/in²	ASTM D 790	8000	4500
Thermal properties					
Deflection temperature under load, Unannealed	66 psi; 0.157 in	°F	ASTM D 648	194	
Deflection temperature under load, Unannealed	264 psi; 0.157 in	°F	ASTM D 648	122	
Other properties (23 °C)					
Density		lb/in³	ASTM D 792	0.038	
Specific gravity		-	ASTM D 792	1.06	

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications



## Durethan BC304 000000

---

### Disclaimer

#### Disclaimer for commercial products

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

#### Test values

Unless specified to the contrary, the values given have been established on standardized test specimens at room temperature. The figures should be regarded as guide values only and not as binding minimum values. Kindly note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mould/die, the processing conditions and the coloring.

#### Processing note

Under the recommended processing conditions small quantities of decomposition product may be given off during processing. To preclude any risk to the health and well-being of the machine operatives, tolerance limits for the work environment must be ensured by the provision of efficient exhaust ventilation and fresh air at the workplace in accordance with the Safety Data Sheet. In order to prevent the partial decomposition of the polymer and the generation of volatile decomposition products, the prescribed processing temperatures should not be substantially exceeded. Since excessively high temperatures are generally the result of operator error or defects in the heating system, special care and controls are essential in these areas.

#### Conditioning

Conditioning in accordance with ISO 1110 (70 °C; 62 % r.h.)

© LANXESS Performance Materials GmbH | DE 50569 COLOGNE | Germany

