

# Durethan BG30XH3.0LT 904040

PA 6, 30 % glass fibers/glass spheres, injection molding, heat-aging stabilized, low tendency to warp, NIR-laser transparent coloring (black)

ISO Shortname: ISO 16396-PA 6,(GB+GF)30,GHR,S14-060

Property	Test Condition	Unit	Standard	guide value <sup>1</sup>	
				d.a.m.	cond.
Rheological properties					
C Molding shrinkage, parallel	60x60x2; 280 °C / MT 80 °C; 600 bar	%	ISO 294-4	0.5	
C Molding shrinkage, transverse	60x60x2; 280 °C / MT 80 °C; 600 bar	%	ISO 294-4	0.8	
Post- shrinkage, parallel	60x60x2; 120 °C; 4 h	%	ISO 294-4	0.2	
Post- shrinkage, transverse	60x60x2; 120 °C; 4 h	%	ISO 294-4	0.3	
Mechanical properties (23 °C/50 % r. h.)					
C Tensile modulus	1 mm/min	MPa	ISO 527-1,-2	6400	3100
C Tensile Stress at break	5 mm/min	MPa	ISO 527-1,-2	120	65
C Tensile Strain at break	5 mm/min	%	ISO 527-1,-2	4.0	10
C Tensile creep modulus	1 h	MPa	ISO 899-1		2400
C Tensile creep modulus	1000 h	MPa	ISO 899-1		2000
C Charpy impact strength	23 °C	kJ/m²	ISO 179-1eU	45	75
C Charpy impact strength	-30 °C	kJ/m²	ISO 179-1eU	40	45
C Charpy notched impact strength	23 °C	kJ/m²	ISO 179-1eA	< 10	10
C Charpy notched impact strength	-30 °C	kJ/m²	ISO 179-1eA	< 10	< 10
Charpy notched impact strength	-40 °C	kJ/m²	ISO 179-1eA	< 10	< 10
Izod impact strength	23 °C	kJ/m²	ISO 180-1U	35	60
Izod impact strength	-30 °C	kJ/m²	ISO 180-1U	30	40
Izod notched impact strength	-30 °C	kJ/m²	ISO 180-1A	< 10	< 10
Izod notched impact strength	-40 °C	kJ/m²	ISO 180-1A	< 10	< 10
Flexural modulus	2 mm/min	MPa	ISO 178-A	5800	2800
Flexural strength	2 mm/min	MPa	ISO 178-A	185	100
Flexural strain at flexural strength	2 mm/min	%	ISO 178-A	5.0	8.0
Flexural stress at 3.5 % strain	2 mm/min	MPa	ISO 178-A	170	80
C Puncture maximum force	23 °C	N	ISO 6603-2	700	
C Puncture maximum force	-30 °C	N	ISO 6603-2	690	
C Puncture energy	23 °C	J	ISO 6603-2	2.0	
C Puncture energy	-30 °C	J	ISO 6603-2	1.7	
Ball indentation hardness		N/mm²	ISO 2039-1	185	75
Thermal properties					
C Melting temperature	10 °C/min	°C	ISO 11357-1,-3	222	
C Temperature of deflection under load	1.80 MPa	°C	ISO 75-1,-2	190	
C Temperature of deflection under load	0.45 MPa	°C	ISO 75-1,-2	210	
Vicat softening temperature	50 N; 120 °C/h	°C	ISO 306	> 200	
C Coefficient of linear thermal expansion, parallel	23 to 55 °C	10 <sup>-4</sup> /K	ISO 11359-1,-2	0.3	
C Coefficient of linear thermal expansion, transverse	23 to 55 °C	10 <sup>-4</sup> /K	ISO 11359-1,-2	0.9	
C Burning behavior UL 94	1.5 mm	Class	UL 94	HB	
Glow wire test (GWFI)	2.0 mm	°C	IEC 60695-2-12	650	
Burning behavior US-FMVSS302			ISO 3795	passed	



# Durethan BG30XH3.0LT 904040

Property	Test Condition	Unit	Standard	guide value <sup>1</sup> d.a.m. cond.
<b>Electrical properties (23 °C/50 % r. h.)</b>				
C Relative permittivity	100 Hz	-	IEC 60250	4.5
C Relative permittivity	1 MHz	-	IEC 60250	4.0
C Dissipation factor	100 Hz	10 <sup>-4</sup>	IEC 60250	265
C Dissipation factor	1 MHz	10 <sup>-4</sup>	IEC 60250	220
C Volume resistivity		Ohm·m	IEC 60093	1E13
C Surface resistivity		Ohm	IEC 60093	1E14
C Comparative tracking index CTI	Solution A	Rating	IEC 60112	375
<b>Other properties (23 °C)</b>				
C Water absorption (Saturation value)	Water at 23 °C	%	ISO 62	7
C Water absorption (Equilibrium value)	23 °C; 50 % RH	%	ISO 62	2.2
C Density		kg/m <sup>3</sup>	ISO 1183	1355
Bulk density		kg/m <sup>3</sup>	ISO 60	700
<b>Processing conditions for test specimens</b>				
C Injection molding-Melt temperature		°C	ISO 294	280
C Injection molding-Mold temperature		°C	ISO 294	80
<b>Processing recommendations</b>				
Drying temperature dry air dryer		°C	-	80
Drying time dry air dryer		h	-	2-6
Residual moisture content		%	Acc. to Karl Fischer	0.03-0.12
Melt temperature (Tmin - Tmax)		°C	-	270-290
Mold temperature		°C	-	80-120

## Notes

**1** Typical properties: these are not to be construed as specifications

**C** These property characteristics are taken from the CAMPUS plastics data bank and are based on the international catalogue of basic data for plastics according to ISO 10350.



## Durethan BG30XH3.0LT 904040

---

### Disclaimer

#### Disclaimer for commercial products

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

#### Test values

Unless specified to the contrary, the values given have been established on standardized test specimens at room temperature. The figures should be regarded as guide values only and not as binding minimum values. Kindly note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mould/die, the processing conditions and the coloring.

#### Processing note

Under the recommended processing conditions small quantities of decomposition product may be given off during processing. To preclude any risk to the health and well-being of the machine operatives, tolerance limits for the work environment must be ensured by the provision of efficient exhaust ventilation and fresh air at the workplace in accordance with the Safety Data Sheet. In order to prevent the partial decomposition of the polymer and the generation of volatile decomposition products, the prescribed processing temperatures should not be substantially exceeded. Since excessively high temperatures are generally the result of operator error or defects in the heating system, special care and controls are essential in these areas.

#### Conditioning

Conditioning in accordance with ISO 1110 (70 °C; 62 % r.h.)

© LANXESS Performance Materials GmbH | DE 50569 COLOGNE | Germany

