

# Pocan C5211 000000

PBT+PC, 10% mineral, injection molding, low tendency to warp, improved surface finish, improved impact strength

ISO Shortname: ISO 20028-PBT+PC,MD10,GHMPR,09-030

Property	Test Condition	Unit	Standard	guide value <sup>1</sup>
<b>Rheological properties</b>				
C Melt volume-flow rate	270 °C; 5 kg	cm <sup>3</sup> /(10 min)	ISO 1133-1	45
C Molding shrinkage, parallel	60x60x2	%	ISO 294-4	0.7
C Molding shrinkage, transverse	60x60x2	%	ISO 294-4	0.7
Post- shrinkage, parallel	60x60x2	%	ISO 294-4	0.5
Post- shrinkage, transverse	60x60x2	%	ISO 294-4	0.4
<b>Mechanical properties (23 °C/50 % r. h.)</b>				
C Tensile modulus	1 mm/min	MPa	ISO 527-1,-2	3300
C Tensile Stress at break	5 mm/min	MPa	ISO 527-1,-2	50
C Tensile Strain at break	5 mm/min	%	ISO 527-1,-2	12
C Charpy impact strength	23 °C	kJ/m <sup>2</sup>	ISO 179-1eU	200
C Charpy impact strength	-30 °C	kJ/m <sup>2</sup>	ISO 179-1eU	150
C Charpy notched impact strength	23 °C	kJ/m <sup>2</sup>	ISO 179-1eA	7
C Charpy notched impact strength	-30 °C	kJ/m <sup>2</sup>	ISO 179-1eA	7
Izod impact strength	23 °C	kJ/m <sup>2</sup>	ISO 180-1U	140
Izod impact strength	-30 °C	kJ/m <sup>2</sup>	ISO 180-1U	100
Izod notched impact strength	23 °C	kJ/m <sup>2</sup>	ISO 180-1A	7
Izod notched impact strength	-30 °C	kJ/m <sup>2</sup>	ISO 180-1A	7
Flexural modulus	2 mm/min	MPa	ISO 178-A	3550
Flexural strength	2 mm/min	MPa	ISO 178-A	95
Flexural strain at flexural strength	2 mm/min	%	ISO 178-A	5.2
Flexural stress at 3.5 % strain	2 mm/min	MPa	ISO 178-A	90
<b>Thermal properties</b>				
C Melting temperature	10 °C/min	°C	ISO 11357-1,-3	225
C Temperature of deflection under load	1.80 MPa	°C	ISO 75-1,-2	100
C Temperature of deflection under load	0.45 MPa	°C	ISO 75-1,-2	120
Vicat softening temperature	50 N; 120 °C/h	°C	ISO 306	130
C Coefficient of linear thermal expansion, parallel	23 to 55 °C	10 <sup>-4</sup> /K	ISO 11359-1,-2	0.8
C Coefficient of linear thermal expansion, transverse	23 to 55 °C	10 <sup>-4</sup> /K	ISO 11359-1,-2	0.7
<b>Other properties (23 °C)</b>				
C Density		kg/m <sup>3</sup>	ISO 1183	1290
Bulk density		kg/m <sup>3</sup>	ISO 60	700
<b>Processing conditions for test specimens</b>				
C Injection molding-Melt temperature		°C	ISO 294	270
C Injection molding-Mold temperature		°C	ISO 294	80
<b>Processing recommendations</b>				
Drying temperature circulating air dryer		°C	-	120
Drying time circulating air dryer		h	-	4-8
Residual moisture content		%	Acc. to Karl Fischer	0.02
Melt temperature (Tmin - Tmax)		°C	-	260-280



## Pocan C5211 000000

Property	Test Condition	Unit	Standard	guide value <sup>1</sup>
Mold temperature		°C	-	70-100

### Notes

**1** Typical properties: these are not to be construed as specifications

**C** These property characteristics are taken from the CAMPUS plastics data bank and are based on the international catalogue of basic data for plastics according to ISO 10350.



## Pocan C5211 000000

---

### Disclaimer

#### Disclaimer for trial products

This is a trial product at the developmental stage. No definitive statements can therefore be made as to type conformity, processability, long-term performance characteristics or other production or application parameters. Therefore, the purchaser/user uses the trial product entirely at his own risk without having been given any warranty or guarantee and agrees that the supplier shall not be liable for any damage, of whatever nature, arising out of such use. Unless specified to the contrary, the values given have been established on standardized test specimens at room temperature. The figures should be regarded as non-binding approximate data only, and not as guide values or binding minimum values. Please note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mold/die, the processing conditions and the coloring. The marketing and continued supply of this material are not assured and may be discontinued at any time. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

#### Test values

Unless specified to the contrary, the values given have been established on standardized test specimens at room temperature. The figures should be regarded as guide values only and not as binding minimum values. Kindly note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mould/die, the processing conditions and the coloring.

#### Processing note

Under the recommended processing conditions small quantities of decomposition product may be given off during processing. To preclude any risk to the health and well-being of the machine operatives, tolerance limits for the work environment must be ensured by the provision of efficient exhaust ventilation and fresh air at the workplace in accordance with the Safety Data Sheet. In order to prevent the partial decomposition of the polymer and the generation of volatile decomposition products, the prescribed processing temperatures should not be substantially exceeded. Since excessively high temperatures are generally the result of operator error or defects in the heating system, special care and controls are essential in these areas.

© Envalior Deutschland GmbH | DE 50569 COLOGNE | Germany

